

D-261NF

Ethylene vinyl acetate emulsion adhesive

**DAEHEUNG CHEMICAL**

D-261NF is ethylene-vinyl acetate copolymer emulsion as an adhesive, it is possible in a variety of insulation material and is excellent in flame retardation required area, and adhesion with the PVC sheet is a flame-retardant performance, and workability is excellent product.

1. Uses

- Plywood bonding for soft PVC film or semi rigid PVC sheet.
- Insulation and bonding of soft PVC FILM
- SEMI RIGID FILM adhesion

2. Characteristics

- Excellent in initial and final bonding strength.
- Very good workability.
- Good strength of bonding for PVC film.
- Domestic demand and weather resistance is good.
- Excellent flame retardant.

3. Physical properties

Properties	Value
Main component	Ethylene vinyl acetate copolymer
Color	Milk-white and viscous liquid
pH	6~8
Solid contents	63.5±1 % (at 105±5°C, 3hr)
Viscosity	17,000~18,000 cps (at 20°C, RION VT-04 #2)
Shelf life	9 months in unbroken package under dry and cool condition

4. How to use

- Remove all dirt, grease, water and rust from the bonding surface before applying.
- Wood, room and glue temperature: 15 ~ 25 °C
- Wood moisture: 8 ~ 12 %
- Humidity: 65 ~ 75 % RH

● Applied amount

PVC film 0.2 mm below	90 ~ 120 g/m ²
PVC film 0.2 mm up	120 ~ 150 g/m ²
Emboss PVC film	110 ~ 130 g/m ²

● Dry

- Open time 20min
- Prohibit the re-bonding.

● Pressure

PVC film 0.2 mm below	0.5 ~ 1.0 kg/cm ²
PVC film 0.2 mm up	1.0 ~ 3.0 kg/cm ²
Emboss PVC film	0.5 kg/cm ²

● Curing

- Press time: 1~2 hr up
- Press temperature: 15~20 °C

5. Caution

- Avoid direct rays of the sun and keep in cool and dry place.
- The brush and other tools for spreading the adhesive, the stain parts and hands, etc, should be cleaned by wiping or washing with water.
- Use with adequate ventilation.
- Store at room temperature.
- Close the cap tightly after using it.
- Don't use except for the original purpose.

6. Packaging

- 18kg CAN

Please contact us for further information or see Material Safety Data Sheet (MSDS) for this product.

DAEHEUNG CHEMICAL CO., LTD.

68, Sandan-ro 64beon-gil, Pyeongtaek-si,

Gyeonggi-do, Korea

Telephone +82-2-554-8211, +82-31-668-1424

Facsimile +82-2-554-8215, +82-31-668-1425

Website www.dhcbond.co.kr



DAEHEUNG CHEMICAL