SR 3300





SR 3300 is one component heat resistant silicone sealant. It has excellent workability, durability and weatherability.

1. Uses

- Sealing of heat resistant part.
- Sealing of duct, boiler joint.
- Sealing of heat resistant & cold-proof part and outdoor equipment.

2. Characteristics

- Working on temperatures of a wide range [low (-50 °C) and high (250 °C)].
- Resistant to instantaneous temperature of 300 ℃
- Excellent weatherability and chemical resistance.
- Not stimulate such as acetic acid.

3. Physical properties

Properties	Value
Main component	Silicone polymer
Curing system	Moisture curing
Curing type	Oxime
Appearance	Soft paste
Color	Gray, Red(Order made color)
Specific gravity	1.34~1.44(Red: 1.00~1.08)
Tack free time	Max. 5 min(23℃, 50% RH)
Curing full time	72hr(3mm / 23 °C , 50% RH)
Hardness	30~40(Red 15~25) (Shore A)
Tensile strength	Min. 1.0 N/mm ² (ASTM D412)
Elongation	Min. 300%(ASTM D412)
Temperature resistance	-50℃~250℃
Shelf life	1 year in unbroken package under dry and cool condition(5~25℃)

4. How to use

Joint

Check the joint that is considered the seal and repair of the construction materials that draw the plan.

Clean and dry

Clean and remove oil, dust, impurities on surface..

Masking tape

Use masking tape to protect adjacent surfaces.

Back-Up material installation

Back-up material is the polyethylene foam or polyurethane foam .

Primer

Primer can be used only when it is necessary. It can also be used to increase, its supplementary of adhesive strength if a sealant can't get an adhesive strength.

Sealant caulking

Apply positive pressure adequate to properly fill and seal the joint width.

Tooling

Shave the surface of the sealant in same angel by the rubber knife or scoop.

Masking tape & Sealant cleaning

When the tooling is over, just remove the masking tape.

Excess sealant should be cleaned from glass, metal, plastic surfaces while still uncured.

If it is cured, please use the knife.

5. Caution

- The cartridge should not be exposed to direct sunlight & shall be kept in a cool and dry place.
- Use with adequate ventilation and avoid prolonged breathing of vapors.
- Prolonged or repeated skin contact might cause irritation.
- In the event of eye contact wash thoroughly with water and consult a physician immediately.
- Don't use except for the original purpose.
- Don't use to mix with hot-melt.
- Don't use double-layer glass, fishbowl, professional SPEC.

6. Packaging

100ml TUBE / 280ml cartridge

Please contact us for further information or see Material Safety Data Sheet (MSDS) for this product.

DAEHEUNG CHEMICAL CO., LTD.

430-8 Mogokdong, Pyongtaeksi, Gyeonggido, Korea

Telephone +82-2-554-8211, +82-31-663-5251

Facsimile +82-2-554-8215, +82-31-664-3361

Website www.dhcbond.com

